

Appl. No. 10/756,558
December 27, 2005
Response to Office action of September 30, 2005

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (currently amended) A method of testing cement comprising:
introducing cement into a curing vessel that is at least partially inside a test vessel, the curing vessel comprising a flexible sleeve;
adjusting the cement temperature and pressure to a selected temperature and pressure while maintaining substantially no pressure differential between the inside and the outside of the flexible sleeve;
curing the cement at a the selected temperature and pressure;
maintaining the cement at least at the selected temperature and pressure after the cement has cured and until testing of the cement; and
testing the cement for a performance property.
2. (currently amended) The method of claim 1 further comprising the curing vessel being filled with a curing vessel fluid and the test vessel being filled with a test vessel fluid before introducing the cement into the curing vessel such that there is substantially no pressure differential between the inside and the outside of the ~~curing vessel~~ flexible sleeve.
3. (currently amended) The method of claim 1 further comprising:
displacing a curing vessel fluid from the curing vessel when introducing the cement into the curing vessel, the test vessel being at the selected temperature and pressure; and
maintaining there being substantially no pressure differential between the inside and outside of the ~~curing vessel~~ flexible sleeve as the cement is introduced into the curing vessel.
4. (original) The method of claim 3 further comprising:
comparing the cement going into the curing chamber with the material being displaced out of the curing vessel to verify that no curing vessel fluid remains in the curing chamber; and
placing a selected curing vessel fluid head on the cement.

Appl. No. 10/756,558
December 27, 2005
Response to Office action of September 30, 2005

5. (canceled)

6. (currently amended) The method of claim 1 further comprising introducing the cement through a first fluid line controlled by a first valve, the curing vessel further comprising first and second end caps ~~and a engageable with the flexible sleeve adapted~~ to contain the cement within the curing vessel.

7. (canceled)

8. (currently amended) The method of claim 1 further comprising allowing the pressure differential between the inside and the outside of the ~~curing vessel~~ flexible sleeve to adjust as the cement cures.

9. (original) The method of claim 1 further comprising maintaining the pressure in the test vessel above 5000 pounds per square inch while the cement cures.

10. (original) The method of claim 1 further comprising maintaining the pressure in the test vessel with a pressure regulator.

11. (original) The method of claim 1 further comprising maintaining the temperature in the test vessel above 250 °F while the cement cures.

12. (original) The method of claim 1 further comprising maintaining the temperature in the test vessel with a heating jacket around the test vessel.

13. (currently amended) The method of claim ~~6~~1 further comprising measuring the change in volume of the cement in the curing vessel during curing.

14. (original) The method of claim 13 further comprising measuring the change of the cement in the radial dimension with a first strain gauge and measuring the change of the cement in the axial

Appl. No. 10/756,558
December 27, 2005
Response to Office action of September 30, 2005

dimension with a second strain gauge.

15. (currently amended) The method of claim 14 further comprising:

the curing vessel further comprising first and second end caps engageable with the flexible sleeve to contain the cement within the curing vessel; and

the first strain gauge measuring the change of the ~~curing vessel~~ flexible sleeve in the radial dimension and the second strain gauge measuring the change of at least one of the first and second end caps in the axial dimension.

16. (original) The method of claim 1 where the testing of the cement comprises a test selected from the group consisting of hydrostatic, unconfined, confine, uni-axial, hydrostatic cycling, confine axial, shear bonding, and pore pressure cycling.

17. (original) The method of claim 1 where the testing of the cement comprises a test measuring a parameter selected from the group consisting of axial pressure, radial pressure, pore pressure, axial strain, circumferential strain, longitudinal acoustic velocity, shear acoustic velocity, water of hydration, heat of hydration, and permeability.

18. (original) The method of claim 1 where the performance property is selected from the group consisting of Young's Modulus, Poisson's Ratio, Fatigue, Failure Strength, Dynamic Young's Modulus, and Dynamic Poisson's Ratio.

19. (original) The method of claim 1 further comprising testing the cement by adjusting the pressure inside the curing vessel with a pressure fluid inlet line.

20. (original) The method of claim 1 further comprising testing the cement by adjusting the volume of the curing vessel.

21. (original) The method of claim 20 further comprising adjusting the volume of the curing vessel by moving at least one of a first and second curing vessel end cap.

Appl. No. 10/756,558
December 27, 2005
Response to Office action of September 30, 2005

22. (currently amended) The method of claim 1[,], wherein the curing vessel comprising further comprises first and second end caps and a engageable with the flexible sleeve adapted to contain the cement within the curing vessel.

23. (currently amended) The method of claim 22-1 where the flexible sleeve is rubber.

24. (currently amended) The method of claim 23-1 where the flexible sleeve is Viton-a fluoroelastomer.

25. (currently amended) A method of testing cement comprising:

introducing a curing vessel fluid into a curing vessel that is at least partially inside a test vessel, the curing vessel comprising a flexible sleeve;

adjusting the curing vessel fluid temperature and pressure to a selected temperature and pressure while maintaining substantially no pressure differential between the inside and the outside of the flexible sleeve;

displacing a curing vessel fluid from within a-the curing vessel by introducing cement into the curing vessel, the curing vessel being at least partially inside a test vessel at a selected temperature and pressure- while maintaining substantially no pressure differential between the inside and the outside of the flexible sleeve as the cement is introduced into the curing vessel;

maintaining substantially no pressure differential between the inside and the outside of the curing vessel as the cement is introduced into the curing vessel;

curing the cement at the selected temperature and pressure;

maintaining the cement at least at the selected temperature and pressure after the cement has cured and until testing of the cement; and

testing the cement for a performance property.

26. (original) The method of claim 25 further comprising the test vessel being filled with a test vessel fluid.

Appl. No. 10/756,558
December 27, 2005
Response to Office action of September 30, 2005

27. (canceled)

28. (original) The method of claim 25 further comprising:
comparing the cement going into the curing vessel with the material being displaced out
of the curing vessel to verify that no curing vessel fluid remains in the curing vessel; and
placing a selected curing vessel fluid head on the cement.

29. (currently amended) The method of claim 25 further comprising introducing the cement
through a first fluid line controlled by a first valve, the curing vessel further comprising first and second
end caps ~~and a engageable with the flexible sleeve adapted~~ to contain the cement within the curing
vessel.

30. (currently amended) The method of claim 25 further comprising allowing the pressure
differential between the inside and the outside of the ~~curing vessel~~ flexible sleeve to adjust as the
cement cures.

31. (original) The method of claim 25 further comprising maintaining the pressure in the test
vessel above 5000 pounds per square inch while the cement cures.

32. (original) The method of claim 25 further comprising maintaining the pressure in the test
vessel with a pressure regulator.

33. (original) The method of claim 25 further comprising maintaining the temperature in the
test vessel above 250 °F while the cement cures.

34. (original) The method of claim 25 further comprising maintaining the temperature in the
test vessel with a heating jacket around the test vessel.

35. (currently amended) The method of claim ~~29~~ 25 further comprising measuring the change in
volume of the cement in the curing vessel during curing.

Appl. No. 10/756,558
December 27, 2005
Response to Office action of September 30, 2005

36. (original) The method of claim 35 further comprising measuring the change of the cement in the radial dimension with a first strain gauge and measuring the change of the cement in the axial dimension with a second strain gauge.

37. (currently amended) The method of claim 36 further comprising:
the curing vessel further comprising first and second end caps engageable with the flexible sleeve to contain the cement within the curing vessel; and
the first strain gauge measuring the change of the ~~curing vessel~~-flexible sleeve in the radial dimension and the second strain gauge measuring the change of at least one of the first and second end caps in the axial dimension.

38. (original) The method of claim 25 where the testing of the cement comprises a test selected from the group consisting of hydrostatic, unconfined, confine, uni-axial, hydrostatic cycling, confine axial, shear bonding, and pore pressure cycling.

39. (original) The method of claim 25 where the testing of the cement comprises a test measuring a parameter selected from the group consisting of axial pressure, radial pressure, pore pressure, axial strain, circumferential strain, longitudinal acoustic velocity, shear acoustic velocity, water of hydration, heat of hydration, and permeability.

40. (original) The method of claim 25 where the performance property is selected from the group consisting of Young's Modulus, Poisson's Ratio, Fatigue, Failure Strength, Dynamic Young's Modulus, and Dynamic Poisson's Ratio.

41. (original) The method of claim 25 further comprising testing the cement by adjusting the volume of the curing chamber.

42. (original) The method of claim 41 further comprising adjusting the volume of the curing chamber by moving at least one of a first and second curing vessel end caps.

Appl. No. 10/756,558
December 27, 2005
Response to Office action of September 30, 2005

43. (currently amended) The method of claim 25[,] wherein the curing vessel comprising further comprises first and second end caps and a engageable with the flexible sleeve adapted to contain the cement within the curing vessel.

44. (currently amended) The method of claim ~~43~~25 where the flexible sleeve is rubber.

45. (currently amended) The method of claim ~~44~~25 where the flexible sleeve is ~~Viton~~a fluoroe elastomer.

46. (currently amended) A method of testing cement comprising:
introducing cement into a curing vessel at least partially inside a test vessel, the curing vessel comprising a flexible sleeve;
placing a selected curing vessel fluid head on the cement;
~~increasing~~adjusting the temperature and pressure of the test vessel to a selected temperature and pressure while ~~continuing to maintain~~maintaining substantially no pressure differential between the inside and the outside of the ~~curing vessel~~flexible sleeve until the test vessel reaches the selected temperature and pressure;
curing the cement at a ~~the~~ selected temperature and pressure;
maintaining the cement at least at the selected temperature and pressure after the cement has cured and until testing of the cement; and
testing the cement for a performance property.

47. (currently amended) The method of claim 46 further comprising introducing the cement through a first fluid line controlled by a first valve, the curing vessel further comprising first and second end caps ~~and a engageable with the flexible sleeve adapted to contain the cement within the curing vessel.~~

48. (canceled)

Appl. No. 10/756,558
December 27, 2005
Response to Office action of September 30, 2005

49. (currently amended) The method of claim 46 further comprising allowing the pressure differential between the inside and the outside of the ~~curing vessel~~ flexible sleeve to adjust as the cement cures.

50. (original) The method of claim 46 further comprising maintaining the pressure in the test vessel above 5000 pounds per square inch while the cement cures.

51. (original) The method of claim 46 further comprising maintaining the pressure in the test vessel with a pressure regulator.

52. (original) The method of claim 46 further comprising maintaining the temperature in the test vessel above 250 °F while the cement cures.

53. (original) The method of claim 46 further comprising maintaining the temperature in the test vessel with a heating jacket around the test vessel.

54. (currently amended) The method of claim ~~47~~ 46 further comprising measuring the change in volume of the cement in the curing vessel during curing.

55. (original) The method of claim 54 further comprising measuring the change of the cement in the radial dimension with a first strain gauge and measuring the change of the cement in the axial dimension with a second strain gauge.

56. (currently amended) The method of claim 55 further comprising:
the curing vessel further comprising first and second end caps engageable with the flexible sleeve to contain the cement within the curing vessel; and
the first strain gauge measuring the change of the ~~curing vessel~~ flexible sleeve in the radial dimension and the second strain gauge measuring the change of at least one of the first and second end caps in the axial dimension.

Appl. No. 10/756,558
December 27, 2005
Response to Office action of September 30, 2005

57. (original) The method of claim 46 where the testing of the cement comprises a test selected from the group consisting of hydrostatic, unconfined, confine, uni-axial, hydrostatic cycling, confine axial, shear bonding, and pore pressure cycling.

58. (original) The method of claim 46 where the testing of the cement comprises a test measuring a parameter selected from the group consisting of axial pressure, radial pressure, pore pressure, axial strain, circumferential strain, longitudinal acoustic velocity, shear acoustic velocity, water of hydration, heat of hydration, and permeability.

59. (original) The method of claim 46 where the performance property is selected from the group consisting of Young's Modulus, Poisson's Ratio, Fatigue, Failure Strength, Dynamic Young's Modulus, and Dynamic Poisson's Ratio.

60. (original) The method of claim 46 further comprising testing the cement by adjusting the volume of the curing chamber.

61. (original) The method of claim 60 further comprising adjusting the volume of the curing chamber by moving at least one of a first and second curing vessel end caps.

62. (currently amended) The method of claim 46[,] wherein the curing vessel comprising further comprises first and second end caps and a engageable with the flexible sleeve adapted to contain the cement within the curing vessel.

63. (currently amended) The method of claim ~~62~~46 where the flexible sleeve is rubber.

64. (currently amended) The method of claim ~~63~~46 where the flexible sleeve is ~~Viton~~a fluoroelastomer.

65. (original) A testing apparatus for testing cement comprising:
a test vessel comprising a fluid-filled test chamber;

Appl. No. 10/756,558
December 27, 2005
Response to Office action of September 30, 2005

a curing vessel at least partially within the test chamber comprising a first end cap, a second end cap, and a flexible sleeve, the curing vessel being sealed from the fluid in the test chamber; and
the first and second end caps adapted to selectively adjust the volume of the curing vessel.

66. (original) The testing apparatus of claim 65 further comprising a radial deformation gauge comprising a radial deformation measurement band around the flexible sleeve and a spring-loaded strain gauge adapted to measure change of the radial deformation band in the radial dimension corresponding to the change in the radial dimension of the flexible sleeve.

67. (original) The testing apparatus of claim 65 where the flexible sleeve is rubber.

68. (currently amended) The testing apparatus of claim 67 where the flexible sleeve is ~~Viton-a~~ fluoroelastomer.

69. (original) The testing apparatus of claim 67 further comprising a first temperature measurement device adapted to measure the temperature of the cement and a second temperature measurement device adapted to measure the temperature of the test chamber.

70. (original) The testing apparatus of claim 65 further comprising a curing vessel inlet line and a curing vessel outlet line adapted to adjust the pressure within the curing vessel.

71. (original) The testing apparatus of claim 65 further comprising a test vessel inlet line adapted to adjust the pressure within the test chamber.

72. (original) The testing apparatus of claim 65 further comprising a first pressure measurement device adapted to measure the pressure inside the curing vessel and a second pressure measurement device adapted to measure the pressure inside the test vessel.

73. (original) The testing apparatus of claim 65 further comprising a heating jacket for adjusting the temperature within the test chamber.

Appl. No. 10/756,558
December 27, 2005
Response to Office action of September 30, 2005

74. (original) The testing apparatus of claim 70 wherein the curing vessel inlet line is in fluid communication with the first end cap and the curing vessel outlet line is in fluid communication with the second end cap.

75. (original) The testing apparatus of claim 74 further comprising a first valve to control flow through the curing vessel inlet line and a second valve to control flow through the curing vessel outlet line.

76. (original) The testing apparatus of claim 65 further comprising an axial deformation gauge comprising a axial strain gauge adapted to measure the axial movement of at least one of the first and second end caps.

77. (new) The method of claim 46 further comprising testing the cement by adjusting the pressure inside the curing vessel with a pressure fluid inlet line.